

**divina fabric –**

designed by Finn Skodt.  
100% new wool from New Zealand,  
Weight: 820 g/lin.m.  
Testing: in excess of 45,000 rubs per Martindale method.  
BS 5690 1991,  
Lightfastness: (ISO) 5-6,  
Piling: (SN) 5,  
Rubfastness: (ISO) dry 4-5, wet 4-5,  
Meets California flame retardant standards.

**elmo soft leather –**

appropriate for public/private use.  
pliable grain leather from Scandanavian cattle.  
excellent durability.  
Thickness: 1.0-1.2mm,  
Lightfastness: (ISO) 6,  
Piling: (SN) 5,  
Rubfastness: (ISO) dry 2000/4 , wet 80/4,  
Finish adhesion: 2 N/CM,  
Tear-Strength: 20 N.  
Meets California flame retardant standards.

**fiori leather –**

cow hide, covered semi aneline leather with rough grain,  
width per m2.

**granula fabric –**

86% Wv/ 8% Pa/ 6% Pe,  
weight 740 g/lin.m.,  
Testing: in excess of 100,000 rubs per Martindale method.  
BS 5852 ignition source 0+1(cigarette + small flame),  
EN 1021 - 1/2 ignition source 0+1(cigarette + small flame),  
Lightfastness: 6-7,  
Piling (SN) 5.

**interglobe wool fabric –**

designed by H. Gabriel and J. Thomsen.  
100% new wool, Weight: 660 g/lin.m.  
Testing: in excess of 50,000 rubs per Martindale method.  
BS 5852 ignition source 0+1(cigarette + match), EN 1021 P1&P2,  
Lightfastness: (ISO) 5-7,  
Piling: (SN) 4,  
Rubfastness: (ISO) wet/dry 4-4.

**ohmann leer fabric –**

south german cattle hides,  
thickness 1,0 - 1,2 mm,  
Testing: in excess of 20,000 rubs per Martindale method.  
flame resistance, EN (ISO) 8191 1&2.  
Lightfastness: (ISO) 5.  
Rubfastness: (ISO) >4



[www.unicahome.com](http://www.unicahome.com)  
1-888-89-UNICA

**sandstone fabric –**

65% Co/ 18% Vi/ 13% Wv/ 4% Pa,  
weight 794 g/lin.m.,  
Testing: in excess of 80,000 rubs per Martindale method.  
BS 5852 ignition source 1 (small flame),  
EN 1021-2 ignition source 1 (small flame),  
Lightfastness: 6-7,  
Piling: (SN) 5.

**santos leather –**

cow hide,  
covered semi aniline leather with rough grain,  
width per m2.

**success fabric –**

100% new wool,  
Weight: 629g/lin.m  
Testing in excess of 50,000 rubs per Martindale method.  
Lightfastness: (ISO) 4-5,  
Piling: (SN) 4,  
Rubfastness: (ISO) dry 4-5, wet 4-5,

**tonus fabric –**

designed by Nina Koppel.  
90% wool / 10% helanaca,  
Weight: 660g/lin.m.  
Testing: in excess of 50,000 rubs per Martindale method.  
EN ISO 12947:1999  
Lightfastness: (ISO) 5-6,  
Piling: (SN) 5,  
Rubfastness: (ISO) dry 4-5, wet 4-5,  
Meets California flame retardant standards.



[www.unicahome.com](http://www.unicahome.com)  
1-888-89-UNICA